

Bituminous Black Paint

Date: 18 November 2016

Fact Sheet No.: TDS00383

YOUR SMART ADVANTAGES

- For metalwork and roofs
- For wood, metal, roofing felt & cement
- Brush on

USES

Bostik Bituminous Black Paint is a protective coating for external waterproofing and weather protection for use on ferrous and non-ferrous metals, concrete, roofing felt, fibre cement, corrugated iron, asphalt and wood.

PRODUCT CHARACTERISTICS

Colour	Black
Form	Low viscosity liquid
Specific Gravity	0.9 approx.
Composition	A bitumen solution
Product Codes	30812217 1 Litre x 6 30812218 2.5 Litre x 4 30812219 5 Litre 30812221 22.5 Litre
Storage/Shelf Life	Store and transport this container in a secure upright position. Ensure the lid is secure. Store for up to 24 months from date of manufacture in original, unopened packaging under cool, dry conditions within the temperature range of +5°C to +35°C and out of direct sunlight.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+5°C to +35°C
Coverage	4 - 6m ² per litre, depending on porosity of the surface
Drying Times	Touch dry in approximately 6 hours Fully dry in approximately 24 hours
Solvent for Cleaning Up	Proprietary brush cleanser Hardened material may be removed by soaking in cleanser

DIRECTIONS FOR USE

IMPORTANT: Before using Bostik Bituminous Black Paint refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

PREPARATION

1. Ensure the roof surface is structurally sound, clean, dry and free from oil, dirt, grease and loose material.
2. Remove any organic growth i.e. moss or lichen with Bostik Fungicidal Wash.
3. Metal surfaces should be wire brushed to remove rust. Any residual rust should be primed with Bostik Penetration Primer for Roofs and allowed to dry for 24 hours.
4. Surfaces to be treated must be completely free of water.

APPLICATION

5. Bostik Bituminous Black Paint is ready for use and thinning is not normally necessary. Apply at least two coats by brush allowing each coat to dry (normally 24 hours) before applying the next.

Non-potable water tanks:

6. Apply a minimum of two coats allowing at least 24 hours for drying between each coat. This may be longer depending on conditions. Thoroughly wash out the tank after the final coat has dried.

CLEANING

7. Clean tools and equipment immediately after use with a proprietary brush cleanser.
8. Hardened material may be removed by soaking in cleanser.
9. Wash hands with a suitable resin dissolving hand cleanser.

PRECAUTIONS IN USE

Do not use internally.

Do not apply to ponds, fishponds or swimming ponds.

Do not apply when the surface is too hot.


It is not advisable to work in humid or foggy weather conditions or when there is a risk of rain before the paint has dried.

Colour indicated on pack is a guide only. It is recommended that users apply a small amount of Bostik Bituminous Black Paint in an inconspicuous area and allow to dry to determine colour suitability before commencing work. Shade variations may occur between batches. When completing projects requiring multiple tins please ensure that they are from the same batch.

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.co.uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data Sheet for Bostik Bituminous Black Paint, available at www.bostik.co.uk.



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk

Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	Fax: 01785 241818	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	Fax: 01785 272867	technical.service@bostik.com
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01785 272625	Fax: 01785 212962	stafford.gatehouse@bostik.com



FM 01696
BS EN ISO 9001:2008

Bostik Limited, Common Road, Stafford, ST16 3EH, UK. Tel: +44 (0) 1785 272625 www.bostik.co.uk
Bostik, Evo-Stik & Sealocrete are registered trademarks of Bostik Ltd.